

Schunk Kohlenstofftechnik GmbH
Rodheimer Strasse 59
35452 Heuchelheim, Germany
research.skt@schunk-group.com
www.schunk-group.com

Bulk density	(g/cm ³)	1.90
Flexural strength	(MPa)	40
Compressive strength	(MPa)	50
Young's modulus dynamic	(GPa)	24
flexural		10
Hardness Rockwell HR10/40		100
Thermal conductivity	(W/mK)	55
Coefficient of thermal expansion α 20 - 140 °C (70 - 285 °F)	(10 ⁻⁶ /K)	
xy in plane		15
z through plane		38
Specific electrical resistance xy in plane	($\mu\Omega$ m)	90
z through plane		190
Heat deflection temperature	(°C / °F)	210 °C / 410 °F

bos 04.08

The data shown above are not guaranteed, but typical values based on our experience. It should be understood that a spread of results can occur due to variations in materials and production processes.

Please find the standards for the determination of our material properties at
www.schunk-group.com/skt/dm